



WILLIAMSBURG

SPECIFICATION SHEET

This is a performance leather with a thick, neutral pebble grain and a multi-layered effect, creating a tri-dimensional look with a soft, round hand.

Specific product requirements must be specified by the customer before making a purchase. The results presented are an average of results found across production runs. Eco and Environmental safety conformity to CE 1907/2006 REACH is assured up to the point of shipment. Any further chemical applications made to the product are the customers responsibility and should be checked prior to use.

Hides should not be exposed to temperatures higher than 60°C/140°F. Hides and finished furniture should be stored in dry conditions within a temperature range of 15°C/59°F to 40°C/104°F. Heat guns, shrink wrapping and any other source of direct heat or sunlight must be avoided. Also avoid any wrapping/packaging material that may react with the leather or finished furniture. Use only leather cleaner and protector products as recommended by a leather care specialist. We recommend spot testing any cleaning or care products before full use. Clean stains as quickly as possible.

Please note that some leather products are more susceptible to staining than others. To ensure you're specifying the best product for its intended or for more detailed care and cleaning instructions use please contact a member or your local sales team.

GENERAL DETAILS

| | |
|------------------------|--------------|
| APPLICATION | Furniture |
| RAW MATERIAL | Bovine |
| CLASSIFICATION | Semi-Aniline |
| ORIGIN | Exotic |
| TANNING TYPE | Chrome |
| AVERAGE SIZE M2 / SQFT | 4.8 / 52 |
| THICKNESS | 1.1 - 1.3MM |

CHARACTERISTICS

TEST METHOD

M.U.

PERFORMANCE

| | | | |
|----------------------------------|------------------|---------------------|------------------------------|
| DRY RUB FASTNESS | EN ISO 11640 | Grey scale | Dry 500 cycles > 4 |
| WET RUB FASTNESS | EN ISO 11640 | Grey scale | Wet 80 cycles > 3/4 |
| PERSPIRATION RUB FASTNESS | EN ISO 11640 | Grey scale | Perspiration 50 cycles > 3/4 |
| FINISHING ADHESION | EN ISO 11644 | N/10 MM | > 2 |
| FLEXING ENDURANCE | EN ISO 5402 | Visual | Dry 50,000 cycles |
| COLOUR FASTNESS TO LIGHT | EN ISO 105 - B02 | Blue scale | > 4 |
| TEAR STRENGTH | EN ISO 3377 - 1 | N | > 20 |
| TENSILE STRENGTH | EN ISO 3376 | N/ MM2 | > 10 |
| COLOUR FASTNESS / WATER SPOTTING | EN ISO 15700 | Grey scale | > 3 |
| PH | EN ISO 4045 | Min 3,2 - | Pass |
| Δ PH | EN ISO 4045 | Δ PH ≤ 0,7 if PH <4 | Pass |
| BURNING TO CIGARETTE / MATCH | BS 5852:1979 | | Pass |
| | BS EN 1021-1 | | Pass |
| | EN 1021-2 | | Pass |

CHEMICAL CHARACTERISTICS

Conforms with REACH regulations

CONTACT

For further queries please call - +1 336 763 0826 or email - sales.usa@crestleather.com